

Paper Specification

SORA FACE

TS - 10-10-2010

(In development)

Parameter	Standard	70	80	90	100	Tolerance
Grammage [g/m ²]	ISO 536	70	80	90	100	± 2
Spec.volume [μm]	DIN 53105	0,95	0,95	0,95	0,95	± 0,05
Smoot.Bendtsen – top side [ml/min]	ISO 8791- 2	30	30	30	30	± 30
Rel. humidity [%]	DIN 19306	47,5	47,5	47,5	47,5	± 7,5
Brightness – top side R 457nm (UV radiation included) [%]	ISO 2470 (D65/10°)	94	94	94	94	± 2
Opacity [%]	ISO 2471	89	91	93	95	± 2

Given values can be used as guide values only and can be changed without prior notice.